

# **T-FIT®** Process

Impact of insulation cladding on personal protection performance





Traditional insulation systems are often clad with an outer layer to protect the insulation from physical and environmental damage, such as the absorption of moisture, as well as providing uniform aesthetics across the system.

Metallic cladding, such as aluminium foil, is an efficient conductor of thermal energy and thus when heated to high temperatures can transfer this heat quickly to skin when touched, causing burns. Given the wide use of metallic cladding in insulation applications, specifications tend to limit the outer surface temperature of the insulation to around 60°C to prevent burn injuries sustained by touching the insulation.

Zotefoams have developed a different approach with their T-FIT Process product range, where an aluminium based

composite coated with a PET film is used as outer cladding, replacing traditional metallic foils. See fig.1 below. PET films are plastic materials and thus are much poorer conductors of heat compared to metallic foils. In practice, this means that the outer surface temperature of products clad with aluminium/PET composite films can be higher than 60°C without causing human injury. It is the contact temperature that is important, rather than the surface temperature.

Contact temperature is measured using a thermesthesiometer probe (according to ASTM C 1057), which imitates the finger's thermal response when pressed against a heated surface over a certain time period. This is the temperature we 'feel'.

Surface temperature is measured using devices such as thermocouples, which are electrical conductors fixed to the surface. This is the actual temperature of the surface.

Product	Pipe temperature	Maximum 5 s contact temperature recorded (°C)	Measured surface temperature (°C)
T-FIT Process clad	189	40	78



#### Figure 1

- PET 23µm
- 9µm aluminium
- Glass scrim 2x2
- 20g/m<sup>2</sup> LDPE coating

# T-FIT® Process continued

On test equipment, Zotefoams can demonstrate that an operator can safely touch the surface of a T-FIT Process tube with 6.35 mm wall thickness and clad with aluminium/PET film composite on a pipe with process temperatures of 200°C, even though the measured surface temperature can be as high as 90°C. Injury is not sustained, despite the high surface temperature, because the PET film is an extremely poor conductor. The maximum skin contact temperature measured is only around 40°C after 5 seconds contact (standard reaction time in an industrial

environment). These contact temperatures are deemed safe as they are below the threshold temperature for burn injuries over this time frame.

The widespread use of metallic cladding systems may have given rise to an acceptance that 60°C is the upper surface temperature limit with regards to personal protection, but substitution of this cladding with the composite described above allows operators to be protected even when temperatures exceed this so-called limit.

# **Exclusion of Liability**

Any information contained in this document is, to the best of the knowledge and belief of Zotefoams plc and of Zotefoams Inc. (together herein referred to as ZOTEFOAMS), accurate. Any liability on the part of ZOTEFOAMS or any subsidiary or holding company of ZOTEFOAMS for any loss, damage, costs or expenses directly or indirectly arising out of the use of such information or the use, application, adaptation or processing of any goods, materials or products described herein is, save as provided in ZOTEFOAMS' conditions of sale ("Conditions of Sale"), hereby excluded to the fullest extent permitted by law.

Where ZOTEFOAMS' goods or materials are to be used in conjunction with other goods or materials, it is the responsibility of the user to obtain from the manufacturers or suppliers of the other goods or materials all technical data and other properties relating to those other goods or materials. Save as provided in the Conditions of Sale no liability can be accepted in respect of the use of ZOTEFOAMS' goods or materials in conjunction with any other goods or materials.

Where ZOTEFOAMS' goods or materials are likely to come into contact with foodstuffs or pharmaceuticals, whether directly or indirectly, or are likely to be used in the manufacture of toys, prior written confirmation of compliance with relevant legislative or regulatory standards for those applications may be requested from ZOTEFOAMS, if appropriate. Save as provided in the Conditions of Sale no liability can be accepted for any damage, loss or injury directly or indirectly arising out of any failure by the user to obtain such confirmation or to observe any recommendations given by or on behalf of ZOTEFOAMS.

ZOTEFOAMS MAKES NO WARRANTIES EXPRESS OR IMPLIED, EXCEPT TO THE EXTENT SET OUT IN THE CONDITIONS OF SALE, AND HEREBY SPECIFICALLY EXCLUDES ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE WITH RESPECT TO ANY GOODS, MATERIALS OR PRODUCTS DESCRIBED HEREIN.

Zotefoams plc Management systems are covered by the following:



**Quality** FM 01870 ISO 9001:2015



**Safety**0HS 52538
ISO 45001: 2018



**Environment** EMS 36270 ISO 14001:2015

#### Zotefoams plc

675 Mitcham Road Croydon Surrey CR9 3AL United Kingdom

Tel: +44 (0) 20 8664 1600 Email: t-fitsales@zotefoams.com

### T-FIT Insulation Solutions India Private Limited

810 Shapath V, S.G. Highway Ahmedabad Gujarat 380015

Tel: +91 (0) 7433946464 Email: t-fitindia@zotefoams.com

## Zotefoams T-FIT Material Technology (Kunshan) Co., Ltd

181 Huanlou Road Development Zone, Kunshan City, Jiangsu Pr. China 215333

Tel: +86 (0)512 5012 6001-8001 Email: t-fitchina@zotefoams.com

#### Zotefoams Inc.

55 Precision Drive Walton KY 41094 USA

Tel: +1 (0) 859 371 4025 Free: (800) 362-8358 (US Only) Email: t-fitusa@zotefoams.com T-FIT® and ZOTEK® are registered trademarks of Zotefoams plc. Kynar® is a registered trademark of Arkema Inc.
All rights reserved

Issue 2 Revision 5 April 2021

If you would like more information visit our website www.zotefoams.com

